

Dryflex® 600911

Thermoplastic Elastomer

ELASTO

Message:

Due to their efficient processing, high performance and recyclability, Dryflex Thermoplastic Elastomers (TPEs) have made significant progress in proving themselves as a quality replacement for vulcanised rubber in window and door sealing applications.

Colour and co-extrusion possibilities have further enhanced the design possibilities for gaskets and seals made from TPE. New technologies such as Dryflex XP foamable TPEs and higher temperature resistant grades are providing materials which deal with design, performance and the environmental needs of the future.

We have supplied compounds for gaskets and weatherstrip extrusion for many years and are a trusted partner to the construction industry.

Today, we continue to develop technical material solutions to meet every application need. Some of the potential property spectrum and possibilities are shown below.

General Information	
---------------------	--

Features	Ozone Resistant
	Recyclable Material
	Semi Rigid

Uses	Gaskets
	Glazing
	Seals
	Weatherstripping

Appearance	Black
	Colors Available
	Natural Color

Physical	Nominal Value	Unit	Test Method
----------	---------------	------	-------------

Specific Gravity	1.16	g/cm ³	ASTM D792
------------------	------	-------------------	-----------

Hardness	Nominal Value	Unit	Test Method
----------	---------------	------	-------------

Durometer Hardness (Shore A)	91		ASTM D2240
------------------------------	----	--	------------

Mechanical	Nominal Value	Unit	Test Method
------------	---------------	------	-------------

Tensile Strength			ASTM D638
------------------	--	--	-----------

--	13.0	MPa	
----	------	-----	--

100% Strain	5.00	MPa	
-------------	------	-----	--

300% Strain	6.00	MPa	
-------------	------	-----	--

Tensile Elongation (Break)	600	%	ASTM D638
----------------------------	-----	---	-----------

Elastomers	Nominal Value	Unit	Test Method
------------	---------------	------	-------------

Tear Strength	50.0	kN/m	ASTM D624
---------------	------	------	-----------

Compression Set (23°C, 72 hr)	30	%	ASTM D395
-------------------------------	----	---	-----------

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT