

Trademark PE LLB1918C

Linear Low Density Polyethylene

Trademark Plastics Corporation

Message:

Trademark PE LLB1918C is a linear low density polyethylene product. It is available in North America. The application fields of Trademark PE LLB1918C include bag/lining, packaging, film and food contact applications.

Features include:

Antiblock software

Butene Comonomer

accessible food

Good sealing performance

Puncture resistance

General Information			
Additive	High caking resistance		
Features	Butene comonomer		
	High caking resistance		
	Perforation resistance		
	Good stripping		
	Good heat sealability		
	Compliance of Food Exposure		
Uses	Packaging		
	Films		
	Lining		
	Food packaging		
	Heavy packing bag		
Agency Ratings	FDA 21 CFR 177.1520(c) 3.1a		
Forms	Particles		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	1.0	g/10 min	ASTM D1238
Films	Nominal Value	Unit	Test Method
Film Thickness - Tested	25	µm	ASTM D882
secant modulus			
1% secant, MD: 25 µm, blown film	186	MPa	ASTM D882
1% secant, TD: 25 µm, blown film	190	MPa	ASTM D882
Tensile Strength			ASTM D882
MD: Broken, 25 µm, blown film	45.5	MPa	ASTM D882
TD: Broken, 25 µm, blown film	31.7	MPa	ASTM D882
Tensile Elongation			ASTM D882
MD: Broken, 25 µm, blown film	570	%	ASTM D882

TD: Broken, 25 µm, blown film	730	%	ASTM D882
Dart Drop Impact (25 µm, Blown Film)	110	g	ASTM D1709
Elmendorf Tear Strength			ASTM D1922
MD: 25 µm, blown film	130	g	ASTM D1922
TD: 25 µm, blown film	320	g	ASTM D1922
Optical	Nominal Value		Test Method
Gloss (45°, 25.4 µm, Blown Film)	45		ASTM D2457
Extrusion	Nominal Value	Unit	
Melt Temperature	204 - 232	°C	
Extrusion instructions			

Blow-up ratio: 1.5:1 or higher

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

