

Ducor® DE1040T

Polypropylene Homopolymer

Ducor Petrochemicals BV

Message:

Ducor DE1040T is a polypropylene homopolymer with a narrow/medium molecular weight distribution. The product is nucleated, and shows a very good flowability and excellent stiffness.

Food Contact Applications: This grade is in compliance with most regulations regarding food contact applications (EU, FDA). Specific information is available upon request.

Applications

thinwalled packaging

General Information			
Additive	Nucleating Agent		
Features	Food Contact Acceptable		
	Good Flow		
	High Stiffness		
	Homopolymer		
	Narrow Molecular Weight Distribution		
	Nucleated		
Uses	Thin-walled Packaging		
Agency Ratings	EC 1907/2006 (REACH)		
	EC 1935/2004		
	EN 71-3		
	EU 10/2011		
	EU 2000/53/EC		
	EU 2002/96/EC (WEEE)		
	EU 2005/84/EC		
	EU 94/62/EC		
	FDA 21 CFR 177.1520(a) 1 (i)		
	FDA 21 CFR 177.1520(c) 1.1a		
RoHS Compliance	RoHS Compliant		
Physical	Nominal Value	Unit	Test Method
Density	0.910	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	50	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness (H 358/30)	90.0	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2000	MPa	ISO 527-2/1
Tensile Stress (Yield)	40.0	MPa	ISO 527-2/50

Tensile Strain			ISO 527-2/50
Yield	7.0	%	
Break	> 20	%	
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	1.3	kJ/m ²	
23°C	2.7	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	13	kJ/m ²	
23°C	75	kJ/m ²	
Notched Izod Impact Strength			ISO 180/1A
-30°C	1.5	kJ/m ²	
23°C	2.5	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	105	°C	ISO 75-2/B
1.8 MPa, Unannealed	62.0	°C	ISO 75-2/A
Vicat Softening Temperature			
--	157	°C	ISO 306/A
--	100	°C	ISO 306/B
Melting Temperature (DSC)	163	°C	ISO 3146
Optical	Nominal Value	Unit	Test Method
Haze	67	%	ASTM D1003

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

