

RTP 205 HS

Polyamide 66

RTP Company

Message:

Warning: The status of this material is 'Commercial: Limited Issue'
The data for this material has not been recently verified.
Please contact RTP Company for current information prior to specifying this grade.
RTP 205 HS is a heat stabilized, glass reinforced nylon 6/6. It has improved oxidation resistance at elevated temperatures versus non-heat stabilized materials.

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 30% filler by weight		
Additive	heat stabilizer		
Features	Antioxidation		
	Thermal Stability		
	Thermal stability, good		
RoHS Compliance	Contact manufacturer		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.36	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.40	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.70	%	ASTM D570
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	120		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	10300	MPa	ASTM D638
Tensile Strength			ASTM D638
Yield	179	MPa	ASTM D638
--	179	MPa	ASTM D638
Tensile Elongation (Break)	3.5	%	ASTM D638
Flexural Modulus	8960	MPa	ASTM D790
Flexural Strength			ASTM D790
--	248	MPa	ASTM D790
Yield	248	MPa	ASTM D790
Compressive Strength	155	MPa	ASTM D695
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.18 mm)	110	J/m	ASTM D256
Unnotched Izod Impact (3.18 mm)	1100	J/m	ASTM D4812
Thermal	Nominal Value	Unit	Test Method

Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	260	°C	ASTM D648
1.8 MPa, not annealed	249	°C	ASTM D648
CLTE - Flow	3.6E-5	cm/cm/°C	ASTM D696
Thermal Conductivity	0.50	W/m/K	ASTM C177
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+14	ohms·cm	ASTM D257
Dielectric Strength	20	kV/mm	ASTM D149
Dielectric Constant (1 MHz)	3.80		ASTM D150
Dissipation Factor (1 MHz)	0.016		ASTM D150
Arc Resistance (1.59 mm)	120	sec	ASTM D495
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.59 mm)	HB		UL 94
Additional Information			
The value listed as Flammability, UL 94, was tested in accordance with RTP test standards.Mold Shrinkage, Linear-Flow, ASTM D-955, 0.25in.: 6mil/in.			
Injection	Nominal Value	Unit	
Drying Temperature	79.4	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.20	%	
Suggested Max Regrind	20	%	
Rear Temperature	274 - 288	°C	
Middle Temperature	274 - 288	°C	
Front Temperature	274 - 288	°C	
Mold Temperature	65.6 - 107	°C	
Injection Pressure	82.7 - 124	MPa	
Back Pressure	0.172 - 0.345	MPa	
Screw Speed	50 - 90	rpm	
Clamp Tonnage	6.9 - 11	kN/cm ²	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT