

Nylene® 132L

Polyamide 66

Custom Resins Group

Message:

Unreinforced nylon 6/6 molding resin

Has the high heat and chemical resistance characteristic of nylon 6/6 materials, combined with high flow and easy molding

Suitable for a variety of applications, such as clips, fasteners, levers, bushings, and other uses where heat, chemical, and wear resistance are required

General Information			
Features	Good Chemical Resistance		
	Good Moldability		
	High Flow		
	High Heat Resistance		
Uses	Bushings		
	Fasteners		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.14	g/cm ³	ASTM D792
Molding Shrinkage - Flow	1.3	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (23°C)	82.7	MPa	ASTM D638
Tensile Elongation (Break, 23°C)	50	%	ASTM D638
Flexural Modulus (23°C)	2860	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	53	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	235	°C	
1.8 MPa, Unannealed	90.0	°C	
Peak Melting Temperature	254	°C	ASTM D3418

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

