

LNP™ THERMOCOMP™ RFB66 compound

Polyamide 66

SABIC Innovative Plastics

Message:

LNP THERMOCOMP RFB66 is a compound based on Nylon 66 resin containing Glass Fiber, Milled Glass.

Also known as: LNP* THERMOCOMP* Compound RF-100-12 MG

Product reorder name: RFB66

General Information			
Filler / Reinforcement	Grinding Glass/Fiberglass		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.71	g/cm ³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹	16500	MPa	ASTM D638
Tensile Strength (Break)	152	MPa	ASTM D638
Tensile Elongation (Break)	1.7	%	ASTM D638
Flexural Modulus	13800	MPa	ASTM D790
Flexural Strength	248	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	85	J/m	ASTM D256
Unnotched Izod Impact (23°C)	670	J/m	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 3.20 mm)	250	°C	ASTM D648
NOTE			

1. 50 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT