

ENFLEX S3130A

Thermoplastic Elastomer

ENPLAST Americas, a Ravago Group Company

Message:

30 Shore A TPE (Styrenic Block Copolymer based) available in both black and natural for injection molding and extrusion applications. This grade offers soft/tactile feel, adhesion (overmolding or co-extrusion) to Polypropylene and good sealing performance.

General Information			
Features	Low compressive deformability		
	High elasticity		
	Solvent resistance		
	Good UV resistance		
	Recyclable materials		
	Workability, good		
	Good coloring		
	Good adhesion		
	Ozone resistance		
	alkali resistance		
	Alcohol resistance		
	acid resistance		
	Detergent resistance		
	Oil resistance		
	Soft		
Appearance	Black		
	Natural color		
Processing Method	Extrusion		
	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.958	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	2.0	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness			ASTM D2240
Shaw A, 10 seconds, extruded	29		ASTM D2240
Shore A, 10 seconds, injection molding	31		ASTM D2240
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (100% Strain)	0.614	MPa	ASTM D412
Tensile Strength (Break)	3.25	MPa	ASTM D412

Tensile Elongation (Break)	730	%	ASTM D412
Tear Strength	17.5	kN/m	ASTM D624
Compression Set			ASTM D395B
23°C, 22 hr	15	%	ASTM D395B
70°C, 22 hr	45	%	ASTM D395B

Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-59.0	°C	ASTM D746
Dynamic Service Temperature	90	°C	

Injection	Nominal Value	Unit
Drying Temperature	65.6 - 71.1	°C
Drying Time	2.0 - 3.0	hr
Rear Temperature	171 - 199	°C
Middle Temperature	177 - 210	°C
Front Temperature	191 - 221	°C
Nozzle Temperature	199 - 229	°C
Processing (Melt) Temp	199 - 221	°C
Mold Temperature	10.0 - 48.9	°C
Injection Pressure	5.17 - 8.96	MPa
Injection Rate	Fast	
Screw Speed	50 - 200	rpm
Clamp Tonnage	2.8 - 4.8	kN/cm ²
Cushion	5.08 - 12.7	mm

Injection instructions

Holding Time: 5 to 7 Sec.

Extrusion	Nominal Value	Unit
Drying Temperature	65.6 - 71.1	°C
Drying Time	2.0 - 3.0	hr
Hopper Temperature	160 - 177	°C
Cylinder Zone 1 Temp.	171 - 191	°C
Cylinder Zone 3 Temp.	179 - 199	°C
Cylinder Zone 5 Temp.	191 - 210	°C
Adapter Temperature	191 - 210	°C
Melt Temperature	191 - 199	°C
Die Temperature	191 - 210	°C

Extrusion instructions

Screw: L/D 20:1 or greater (L/D 24:1 preferred) Cooling Water: 60 - 85°F (15-30°C) Screw Speed: 100 - 200 rpm Screen Pack: 20/40/60

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

