

Isoplast® 202 LGF40 ETPU

Engineering Thermoplastic Polyurethane

Lubrizol Advanced Materials, Inc.

Message:

Type: Isoplast® 202 LGF 40 is an engineering thermoplastic polyurethane resin.

General Information			
Filler / Reinforcement	Long Glass Fiber,40% Filler by Weight		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.50	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.10 to 0.30	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	12000	MPa	ASTM D638
Tensile Strength			ASTM D638
Yield	186	MPa	
Break	186	MPa	
Tensile Elongation			ASTM D638
Yield	1.8	%	
Break	1.8	%	
Flexural Modulus	10000	MPa	ASTM D790
Flexural Strength	338	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.20 mm)	270	J/m	ASTM D256
Instrumented Dart Impact			ASTM D3763
-29°C	14.0	J	
23°C	17.0	J	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	166	°C	
1.8 MPa, Unannealed	144	°C	
Glass Transition Temperature	138	°C	ASTM D3418
CLTE - Flow	7.0E-6	cm/cm/°C	ASTM D696
Injection	Nominal Value	Unit	
Drying Temperature	80.0 to 100	°C	
Processing (Melt) Temp	240 to 260	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

