

TECOLITE KM-470(G)

Phenolic
KYOCERA Chemical Corporation

Message:

Excellent flammability and Excellent properties. Raising the reliability of parts.
Kyocera Chemical's Phenolic Molding Compounds "TECOLITE" are corresponding to the demand for raising the reliability of apparatus, such as flammability by UL regulation. "TECOLITE" have a good dimension stability under a use severe situation for a long period of time. Therefore, it is preeminent product for reliability parts. It is the best for a plug, commutators, heat-resistant electricity parts, etc.

General Information			
Features	Flame Retardant		
	Good Dimensional Stability		
Uses	Electrical/Electronic Applications		
Appearance	Black		
Physical	Nominal Value	Unit	
Specific Gravity	1.57	g/cm ³	
Molding Shrinkage			
Flow ¹	0.80 to 1.0	%	
Flow ²	0.40 to 0.60	%	
Across Flow ³	0.50 to 0.70	%	
Water Absorption (Equilibrium)	< 0.30	%	
Mechanical	Nominal Value	Unit	
Flexural Strength	88.0 to 108	MPa	
Compressive Strength	225 to 255	MPa	
Thermal	Nominal Value	Unit	
Heat Deflection Temperature	185	°C	
Insulation Resistance			
After Boiling	1.0E+9 to 1.0E+10	ohms	
As Molded	1.0E+10 to 1.0E+11	ohms	
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength	> 10	kV/mm	
Arc Resistance	180	sec	
Comparative Tracking Index	190	V	
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.800 mm)	V-0		UL 94
NOTE			
1.	Injection Molding		
2.	Compression Molding		
3.	Injection Molding		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

