

Reblend® 5510M4 BEIGE18

Polycarbonate + ABS

SO.F.TER. SPA

Message:

PC/ABS alloy, talc filled grade

General Information			
Filler / Reinforcement	Talc		
Uses	Automotive Applications		
Agency Ratings	EC 1907/2006 (REACH)		
Appearance	Beige		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.28	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (260°C/5.0 kg)	20	g/10 min	ASTM D1238
Water Absorption (23°C, 24 hr)	0.20	%	ASTM D570
Ash Content	20	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	4100	MPa	ASTM D638
Tensile Strength (Break)	55.0	MPa	ASTM D638
Tensile Elongation (Break)	4.0	%	ASTM D638
Flexural Modulus	4000	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	55	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	115	°C	ASTM D648
Vicat Softening Temperature	130	°C	ASTM D1525 ¹
Flammability	Nominal Value	Test Method	
Flame Rating (0.800 mm)	HB	UL 94	
Injection	Nominal Value	Unit	
Drying Temperature	90.0	°C	
Drying Time	3.0	hr	
Rear Temperature	230	°C	
Middle Temperature	250	°C	
Front Temperature	260	°C	
Mold Temperature	50.0 to 70.0	°C	
NOTE			

1. Rate A (50°C/h), Loading 2 (50 N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

