

Lupol® GP3400

Polypropylene

LG Chem Ltd.

Message:

Description

General Purpose

Application

Electrical & Electronic, Automotive Parts

General Information			
UL YellowCard	E67171-248664		
Filler / Reinforcement	Mineral,40% Filler by Weight		
Features	General Purpose		
Uses	Automotive Applications		
	Automotive Interior Parts		
	Electrical Parts		
	Electrical/Electronic Applications		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.20	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	10	g/10 min	ASTM D1238
Molding Shrinkage - Flow (3.20 mm)	0.60 to 1.1	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹ (Yield, 3.20 mm)	33.3	MPa	ASTM D638
Tensile Elongation ² (Break, 3.20 mm)	10	%	ASTM D638
Flexural Modulus ³ (6.40 mm)	4510	MPa	ASTM D790
Flexural Strength ⁴ (Yield, 6.40 mm)	55.9	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 6.40 mm)	25	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed, 3.20 mm)	140	°C	ASTM D648
RTI Elec (1.50 mm)	65.0	°C	UL 746
RTI Imp (1.50 mm)	65.0	°C	UL 746
RTI Str (1.50 mm)	65.0	°C	UL 746
Flammability	Nominal Value	Test Method	
Flame Rating (1.50 mm)	HB	UL 94	
Injection	Nominal Value	Unit	
Drying Temperature	70.0 to 80.0	°C	

Drying Time	3.0 to 4.0	hr
Suggested Max Moisture	< 0.010	%
Rear Temperature	190 to 210	°C
Middle Temperature	200 to 230	°C
Front Temperature	200 to 230	°C
Nozzle Temperature	210 to 230	°C
Processing (Melt) Temp	200 to 230	°C
Mold Temperature	40.0 to 60.0	°C
Back Pressure	29.4 to 58.8	MPa
Screw Speed	30 to 60	rpm

NOTE

- | | |
|----|------------|
| 1. | 5.0 mm/min |
| 2. | 5.0 mm/min |
| 3. | 1.3 mm/min |
| 4. | 1.3 mm/min |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT