

Ecomass® 720ZD88

Acrylonitrile Butadiene Styrene

Ecomass Technologies

Message:

Ecomass® 720ZD88 is an Acrylonitrile Butadiene Styrene (ABS) material filled with tungsten. It is available in North America for injection molding.

Important attributes of Ecomass® 720ZD88 are:

Good Toughness

Rigid

General Information			
Filler / Reinforcement	Tungsten		
Features	Good Toughness		
	High Specific Gravity		
	Platable		
	Semi Rigid		
Uses	Radiation Shielding		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	6.00	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.20	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	17.2	MPa	ASTM D638
Tensile Elongation (Break)	1.1	%	ASTM D638
Flexural Modulus	8620	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	53	J/m	ASTM D256
Injection	Nominal Value	Unit	
Drying Temperature	71.1 to 82.2	°C	
Drying Time	2.0 to 4.0	hr	
Processing (Melt) Temp	204 to 249	°C	
Mold Temperature	26.7 to 48.9	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

