

TARFLON™ GZ2510

Polycarbonate
Idemitsu Kosan Co., Ltd.

Message:
Flame-retardant

General Information			
UL YellowCard	E48268-240448		
Filler / Reinforcement	Glass Fiber,10% Filler by Weight		
Features	Flame Retardant		
UL File Number	E48268		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.27	g/cm ³	ISO 1183
Spiral Flow	21.0	cm	Internal Method
Molding Shrinkage			Internal Method
Across Flow : 2.00 mm	0.60	%	
Flow : 2.00 mm	0.40	%	
Water Absorption ¹ (Equilibrium, 23°C, 50% RH)	0.15	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	65		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	80.0	MPa	ISO 527-2
Nominal Tensile Strain at Break	5.0	%	ISO 527-2
Flexural Modulus	3500	MPa	ISO 178
Flexural Stress	120	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	8.0	kJ/m ²	ISO 179
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	142	°C	ISO 75-2/A
CLTE - Flow	4.5E-5	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	> 1.0E+16	ohms · cm	ASTM D257
Electric Strength	> 22	kV/mm	IEC 60243-1
Dielectric Constant (1 MHz)	2.95		IEC 60250
Dissipation Factor (1 MHz)	9.0E-3		IEC 60250
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.50 mm)	V-0		UL 94
Additional Information	Nominal Value		

ISO Shortname	>PC-GF10<	
Injection	Nominal Value	Unit
Drying Temperature	120	°C
Drying Time	5.0 to 8.0	hr
Rear Temperature	260 to 300	°C
Middle Temperature	260 to 300	°C
Front Temperature	260 to 300	°C
Mold Temperature	80.0 to 120	°C
NOTE		
1.	24h	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
 Phone: +86 13424755533
 Email: sales@su-jiao.com
 No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT