

REV Materials 8010-003

Polypropylene

REV Materials

Message:

40% cellulose dispersed in a polypropylene matrix suitable for injection molding applications.

General Information			
Filler / Reinforcement	Fibrous filler, 40% filler by weight		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.05	g/cm ³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	4240	MPa	ASTM D638
Tensile Strength	34.5	MPa	ASTM D638
Tensile Elongation (Break)	2.3	%	ASTM D638
Flexural Modulus	3590	MPa	ASTM D790
Flexural Strength	57.2	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	21	J/m	ASTM D256
Unnotched Izod Impact	130	J/m	ASTM D256
Injection	Nominal Value	Unit	
Rear Temperature	149 - 232	°C	
Middle Temperature	149 - 232	°C	
Front Temperature	149 - 232	°C	
Nozzle Temperature	149 - 232	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT