

SAPYLENE T25GF15HB

Polypropylene
Sahel Chimie Co.

Message:

SAPYLENE T25GF15HB is a Polypropylene material filled with 15% glass fiber and 25% talc. It is available in Africa & Middle East. Primary attribute of SAPYLENE T25GF15HB: Non-Toxic.
Typical applications include:
Automotive
Industrial Applications

General Information			
Filler / Reinforcement		Glass Fiber,15% Filler by Weight Talc,25% Filler by Weight	
Features		Non-Toxic	
Uses		Automotive Applications Industrial Applications	
Physical	Nominal Value	Unit	Test Method
Density	1.20	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	10	g/10 min	ASTM D1238
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D, 23°C)	67		ASTM D2240
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress			ISO 527-2/100
Yield	11.6	MPa	
Break	1.95	MPa	
Tensile Strain (Break)	2.9	%	ISO 527-2/100
Flexural Modulus ¹	2.02	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact ² (23°C)	6.2	J/m	ISO 180
NOTE			
1.	100 mm/min		
2.	1A		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

