

Badamid® A70 H

Polyamide 66

Bada AG

Message:

Heat stabilized, low-viscosity injection moulding grade for highly stressed components

General Information				
Features		Heat Stabilized		
		Low Viscosity		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.14	--	g/cm ³	ISO 1183
Water Absorption				ISO 62
Saturation, 23°C	8.1	--	%	
Equilibrium, 23°C, 50% RH	2.5	--	%	
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus ¹ (23°C)	3200	1600	MPa	ISO 527-2/1
Tensile Stress ² (Yield, 23°C)	85.0	60.0	MPa	ISO 527-2/50
Tensile Strain ³ (Yield, 23°C)	4.4	22	%	ISO 527-2/50
Nominal Tensile Strain at Break ⁴ (23°C)	--	> 50	%	ISO 527-2/50
Flexural Stress ⁵ (23°C)	140	75.0	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength ⁶				ISO 179/1eA
-30°C	4.0	4.0	kJ/m ²	
23°C	6.0	12	kJ/m ²	
Charpy Unnotched Impact Strength ⁷				ISO 179/1eU
-30°C	No Break	No Break		
23°C	No Break	No Break		
Notched Izod Impact Strength ⁸				ISO 180/1A
-30°C	3.0	3.0	kJ/m ²	
23°C	5.0	11	kJ/m ²	
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature ⁹				
0.45 MPa, Unannealed	220	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	80.0	--	°C	ISO 75-2/A

Melting Temperature (DSC) 10	262	--	°C	ISO 3146
CLTE - Flow ¹¹	8.5E-5	--	cm/cm/°C	DIN 53752
Maximum Service Temperature				IEC 216
20000 hrs	130	--	°C	
some hours	230	--	°C	
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity ¹²	1.0E+13	1.0E+10	ohms	IEC 60093
Volume Resistivity ¹³	1.0E+15	1.0E+12	ohms·cm	IEC 60093
Electric Strength ¹⁴	30	25	kV/mm	IEC 60243-1
Relative Permittivity ¹⁵	3.60	5.00		IEC 60250
Dissipation Factor ¹⁶ (1 MHz)	0.024	0.17		IEC 60250
Comparative Tracking Index	550	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Flame Rating				UL 94
0.800 mm ¹⁷	V-2	--		
1.60 mm ¹⁸	V-2	--		
Injection	Dry	Unit		
Drying Temperature	80.0		°C	
Drying Time	2.0 to 4.0		hr	
Processing (Melt) Temp	280 to 300		°C	
Mold Temperature	60.0 to 80.0		°C	
NOTE				
1.	Test Specimen according to ISO 3167, Type A			
2.	Test Specimen according to ISO 3167, Type A			
3.	Test Specimen according to ISO 3167, Type A			
4.	Test Specimen according to ISO 3167, Type A			
5.	80x10x4 mm			
6.	80x10x4 mm			
7.	80x10x4 mm			
8.	80x10x4 mm			
9.	110x10x4 mm			
10.	10 K/min, Compound for moulding			
11.	>=10x10x4 mm			
12.	80x80x1 mm			
13.	80x80x1 mm			
14.	80x80x1 mm			

15.	80x80x1 mm
16.	80x80x1 mm
17.	125x13x0.8 mm
18.	125x13x1.6 mm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

