

Maxxam™ FR PP 301 NATL S-30

Polypropylene
PolyOne Corporation

Message:

Maxxam™ FR flame-retardant polyolefin compounds and masterbatches meet stringent flammability performance requirements defined by industry agencies, including Underwriters Laboratories UL 94 V-2, V-0, and 5VA performance ratings. In addition, many compounds in the Maxxam FR portfolio offer elevated Relative Thermal Index (RTI) ratings.

General Information			
UL YellowCard	E76261-101448071	E76261-101448072	
Features	Flame Retardant		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.980	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) ¹ (230°C/2.16 kg)	27	g/10 min	ASTM D1238
Molding Shrinkage			ASTM D955
Flow	1.0 to 2.0	%	
Across Flow	1.0 to 2.0	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ² (Yield)	29.0	MPa	ASTM D638
Flexural Modulus	1210	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.18 mm, Injection Molded)	21	J/m	ASTM D256A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (0.45 MPa, Unannealed, 3.18 mm)	85.0	°C	ASTM D648
RTI Elec			UL 746
0.410 mm	100	°C	
0.750 mm	110	°C	
1.50 mm	110	°C	
3.00 mm	110	°C	
RTI Imp			UL 746
0.410 mm	90.0	°C	
0.750 mm	105	°C	
1.50 mm	105	°C	
3.00 mm	115	°C	
RTI Str			UL 746
0.410 mm	100	°C	
0.750 mm	110	°C	
1.50 mm	110	°C	

3.00 mm	120	°C
Flammability	Nominal Value	Test Method
Flame Rating		UL 94
0.750 mm	V-0	
3.00 mm	V-0	
0.400 mm	VTM-0	
NOTE		
1.	Procedure A	
2.	Type I, 51 mm/min	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT