

FRIANYL® A3 GF07 V2XI

Polyamide 66

Nilit Plastics

Message:

FRIANYL® A3 GF07 V2XI is a Polyamide 66 (Nylon 66) compound, 7% glass fiber reinforced, flame retardant with halogens, free from antimony trioxide, PBB and PBDE, UL listed V2.

This compound is intended for injection molding.

FRIANYL® A3 GF07 V2XI is primarily designed for the Electrical and Electronic industry. It is also suitable for Automotive or Industrial & Consumer applications.

General Information			
UL YellowCard	E172252-100050096		
Filler / Reinforcement	Glass Fiber,7.0% Filler by Weight		
Additive	Flame Retardant		
Features	Antimony Free		
	Flame Retardant		
	Halogenated		
Uses	Automotive Applications		
	Consumer Applications		
	Electrical/Electronic Applications		
	Industrial Applications		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.30	g/cm ³	ISO 1183
Molding Shrinkage			ISO 294-4
Across Flow : 23°C	0.90	%	
Flow : 23°C	0.70	%	
Water Absorption			ISO 62
23°C, 24 hr	1.2	%	
Saturation, 23°C	6.5	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	3900	MPa	ISO 527-2
Tensile Stress (Yield, 23°C)	75.0	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	4.0	%	ISO 527-2
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	4.5	kJ/m ²	
23°C	5.0	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU

23°C	35	kJ/m ²	
30°C	28	kJ/m ²	
Notched Izod Impact Strength			ISO 180/A
-30°C	4.0	kJ/m ²	
23°C	4.5	kJ/m ²	
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	240	°C	ISO 75-2/B
1.8 MPa, Unannealed	230	°C	ISO 75-2/A
Continuous Use Temperature ¹	120	°C	IEC 60216
Ball Pressure Test			IEC 60695-10-2
125°C	Pass		
165°C	Pass		
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity ²	1.0E+13	ohms	IEC 60093
Volume Resistivity (23°C)	1.0E+15	ohms·cm	IEC 60093
Electric Strength (2.00 mm)	20	kV/mm	IEC 60243-1
Comparative Tracking Index (3.20 mm, Solution A)	400	V	IEC 60112
Needle Flame Test			IEC 60695-11-5
1.00 mm	Pass		
2.00 mm	Pass		
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.400 mm	V-2		
0.800 mm	V-2		
1.60 mm	V-2		
3.20 mm	V-1		
Glow Wire Flammability Index			IEC 60695-2-12
0.800 mm	850	°C	
3.20 mm	960	°C	
Glow Wire Ignition Temperature			IEC 60695-2-13
0.800 mm	875	°C	
3.20 mm	900	°C	
Oxygen Index	34	%	ISO 4589-2
Flammability ³	SE		FMVSS 302
NOTE			
1.	20000 hr		
2.	23°C		
3.	355x100x1mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT