

CYCOLAC™ DL200H resin

Acrylonitrile Butadiene Styrene

SABIC Innovative Plastics

Message:

CYCOLAC DL200H is a hydrostable high heat ABS/PC blend

General Information			
Features	Heat resistance, high		
	Hydrolysis stability		
RoHS Compliance	RoHS compliance		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.11	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR)			
260°C/5.0 kg	25	g/10 min	ASTM D1238
220°C/10.0 kg	9.0	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	2330	MPa	ASTM D638
--	2350	MPa	ISO 527-2/1
Tensile Strength			
Yield ²	47.0	MPa	ASTM D638
Yield	49.0	MPa	ISO 527-2/50
Fracture	40.0	MPa	ISO 527-2/50
Tensile Strain			
Yield	3.9	%	ISO 527-2/50
Fracture ³	70	%	ASTM D638
Fracture	75	%	ISO 527-2/50
Flexural Modulus			
50.0mm span ⁴	2200	MPa	ASTM D790
-- ⁵	2100	MPa	ISO 178
Flexural Stress			
--	75.0	MPa	ISO 178
Yield, 50.0mm span ⁶	77.0	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁷			ISO 179/1eA
-30°C	30	kJ/m ²	ISO 179/1eA
23°C	65	kJ/m ²	ISO 179/1eA
Notched Izod Impact			

23°C	620	J/m	ASTM D256
23°C, 6.40 mm	500	J/m	ASTM D256
-40°C ⁸	21	kJ/m ²	ISO 180/1A
23°C ⁹	56	kJ/m ²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, unannealed, 3.20mm	118	°C	ASTM D648
0.45 MPa, unannealed, 64.0mm span ¹⁰	120	°C	ISO 75-2/Bf
1.8 MPa, unannealed, 3.20mm	96.0	°C	ASTM D648
1.8 MPa, unannealed, 6.40mm	101	°C	ASTM D648
1.8 MPa, unannealed, 64.0mm span ¹¹	96.0	°C	ISO 75-2/Af
Vicat Softening Temperature			
--	112	°C	ISO 306/B50
--	114	°C	ISO 306/B120
Injection	Nominal Value	Unit	
Drying Temperature	98.9 - 104	°C	
Drying Time	3.0 - 4.0	hr	
Drying Time, Maximum	8.0	hr	
Suggested Max Moisture	0.040	%	
Suggested Shot Size	30 - 80	%	
Rear Temperature	249 - 282	°C	
Middle Temperature	254 - 288	°C	
Front Temperature	254 - 288	°C	
Nozzle Temperature	260 - 288	°C	
Processing (Melt) Temp	260 - 288	°C	
Mold Temperature	76.7 - 98.9	°C	
Back Pressure	0.345 - 0.689	MPa	
Screw Speed	40 - 70	rpm	
Vent Depth	0.038 - 0.076	mm	
NOTE			
1.	5.0 mm/min		
2.	Type 1, 5.0 mm/min		
3.	Type 1, 5.0 mm/min		
4.	1.3 mm/min		
5.	2.0 mm/min		
6.	1.3 mm/min		
7.	80*10*4 sp=62mm		
8.	80*10*4		
9.	80*10*4		
10.	80*10*4 mm		
11.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

