

Premier LD02023 - AM

Low Density Polyethylene

Premier Polymers, LLC.

Message:

Premier LD02023 resins are clarity low density polyethylene film resins suitable for blown or cast thin film application. Meets all requirements of the U.S. Food and Drug Administration as specified in 21 CFR 177.1520, covering safe use of polyolefin articles intended for direct food contact.

General Information	
Additive	Medium Antiblock
Features	Food Contact Acceptable
	Low Density
	Medium Antiblocking
Uses	Film
Agency Ratings	FDA 21 CFR 177.1520
Processing Method	Blow Molding
	Casting

Physical	Nominal Value	Unit	Test Method
Density	0.923	g/cm ³	ASTM D4883
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	2.0	g/10 min	ASTM D1238
Films	Nominal Value	Unit	Test Method
Secant Modulus			ASTM D882
MD	207	MPa	
TD	228	MPa	
Tensile Strength			ASTM D882
MD : Break	24.1	MPa	
TD : Break	20.7	MPa	
Tensile Elongation			ASTM D882
MD : Break	250	%	
TD : Break	600	%	
Dart Drop Impact	100	g	ASTM D1709
Elmendorf Tear Strength			ASTM D1922
MD	350	g	
TD	200	g	
Optical	Nominal Value	Unit	Test Method
Haze	5.0	%	ASTM D1003

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT