

Michilene F8100GCMN35

Polypropylene Homopolymer

API Polymers, Inc.

Message:

Michilene F8100GCMN35 is a Polypropylene Homopolymer (PP Homopolymer) product filled with 35% glass\mineral. It is available in North America. Characteristics include:
Chemically Coupled
Homopolymer

General Information			
Filler / Reinforcement	Glass\Mineral,35% Filler by Weight		
Features	Chemically Coupled Homopolymer		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.18	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	5.0	g/10 min	ASTM D1238
Molding Shrinkage - Flow	0.40	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	60.7	MPa	ASTM D638
Tensile Elongation (Break)	3.0	%	ASTM D638
Flexural Modulus - Tangent	5720	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	53	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, Unannealed	143	°C	
1.8 MPa, Unannealed	127	°C	
Injection	Nominal Value	Unit	
Drying Temperature	82.2	°C	
Drying Time	3.0	hr	
Suggested Max Moisture	0.20	%	
Rear Temperature	221	°C	
Middle Temperature	221	°C	
Front Temperature	224	°C	
Nozzle Temperature	227	°C	
Processing (Melt) Temp	227	°C	
Mold Temperature	37.8	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT