

VESTOSINT® 1101 white

Polyamide 12
Evonik Industries AG

Message:

VESTOSINT 1101 white is the standard fluidized bed coating powder based on polyamide 12. It is most suitable for the coating of wire goods.

General Information			
Uses	Coating Applications		
	Wire Jacketing		
Appearance	White		
Forms	Powder		
Physical	Nominal Value	Unit	Test Method
Density	1.06	g/cm ³	ISO 1183
Apparent Density	> 0.50	g/cm ³	ISO 60
Water Absorption			ISO 62
Saturation, 100°C ¹	1.7	%	
Saturation, 23°C ²	1.2	%	
Equilibrium, 23°C, 50% RH	0.50	%	
Particle Size Distribution			ISO 4610
< 32.0 µm		wt%	
< 100.0 µm	> 45.0	wt%	
< 250.0 µm	100.0	wt%	
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore D)	75		ISO 868
Ball Indentation Hardness ³	101	MPa	ISO 2039-1
Mechanical	Nominal Value	Unit	Test Method
Taber Abrasion Resistance (100 Cycles, 500 g, CS-17 Wheel)	< 1.00	mg	ASTM D1242
Thermal	Nominal Value	Unit	Test Method
Melting Temperature (DSC)	176	°C	ISO 3146
CLTE - Flow (23 to 55°C)	1.0E-4	cm/cm/°C	ISO 11359-2
Specific Heat	2270	J/kg/°C	ASTM C351
Thermal Conductivity	0.22 to 0.27	W/m/K	DIN 52612
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+15	ohms · cm	IEC 60093
Electric Strength ⁴	85	kV/mm	IEC 60243-1
NOTE			
1.	Immersion		
2.	96%RH		

3.	H30
4.	K20/P50

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

