

VICTREX® PEEK 150GL30 BLACK

Polyetheretherketone

Victrex plc

Message:

High performance thermoplastic material, 30% glass fibre reinforced PolyEtherEtherKetone (PEEK), semi crystalline, granules for injection moulding, easy flow, FDA food contact compliant, colour black.

Complex geometries with thin cross sections or long flow lengths where higher strength in a static system is required. Low coefficient of thermal expansion. Chemically resistant to aggressive environments, suitable for sterilization for medical and food contact applications.

General Information			
UL YellowCard	E161131-224302	E161131-531779	
Filler / Reinforcement	Glass fiber reinforced material, 30% filler by weight		
Features	Semicrystallization		
	High strength		
	Good disinfection		
	Good liquidity		
	Good chemical resistance		
	Compliance of Food Exposure		
Uses	Non-specific food applications		
	Medical/nursing supplies		
Agency Ratings	FDA Food Exposure, Not Rated		
Appearance	Black		
Forms	Particles		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density ¹	1.52	g/cm³	ISO 1183
Spiral Flow ²	15.0	cm	Internal method
Molding Shrinkage ³			ISO 294-4
Vertical flow direction: 180°C	0.90	%	ISO 294-4
Flow direction: 180°C	0.30	%	ISO 294-4
Water Absorption			ISO 62
23°C, 24 hr, 3.20 mm	0.040	%	ISO 62
Balance, 23°C, 3.20mm, 50% RH	0.30	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore D, 23°C)	87		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C)	12000	MPa	ISO 527-2
Tensile Stress			ISO 527-2
Fracture, 23°C	190	MPa	ISO 527-2

Fracture, 125°C	115	MPa	ISO 527-2
Fracture, 175°C	70.0	MPa	ISO 527-2
Fracture, 225°C	55.0	MPa	ISO 527-2
Fracture, 275°C	40.0	MPa	ISO 527-2
Tensile Strain (Break, 23°C)	2.4	%	ISO 527-2
Flexural Modulus (23°C)	11500	MPa	ISO 178
Flexural Stress (23°C)	270	MPa	ISO 178
Compressive Stress			ISO 604
23°C	250	MPa	ISO 604
120°C	160	MPa	ISO 604
200°C	55.0	MPa	ISO 604
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	7.5	kJ/m ²	ISO 180/A
Unnotched Izod Impact Strength (23°C)	50	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature (1.8 MPa, Unannealed)	335	°C	ISO 75-2/A
Glass Transition Temperature	143	°C	ISO 11357-2
Melting Temperature	343	°C	ISO 11357-3
Linear thermal expansion coefficient			ISO 11359-2
Flow: > 143°C	2.0E-5	cm/cm/°C	ISO 11359-2
Flow: < 143°C	2.0E-5	cm/cm/°C	ISO 11359-2
Lateral: < 143°C	4.5E-5	cm/cm/°C	ISO 11359-2
Lateral: > 143°C	1.1E-4	cm/cm/°C	ISO 11359-2
Specific Heat (23°C)	1700	J/kg/°C	DSC
Thermal Conductivity (23°C)	0.30	W/m/K	ISO 22007-4
RTI Elec	240	°C	UL 746
RTI Imp	220	°C	UL 746
RTI	240	°C	UL 746
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	5.0E+15	ohms · cm	IEC 60093
Dielectric Strength (2.00 mm)	22	kV/mm	IEC 60243-1
Dielectric Constant (23°C, 1 kHz)	3.40		IEC 60250
Comparative Tracking Index	150	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Glow Wire Flammability Index (2.00 mm)	960	°C	IEC 60695-2-12
Fill Analysis	Nominal Value	Unit	Test Method
Melt Viscosity (400°C)	290	Pa · s	ISO 11443
Injection	Nominal Value	Unit	
Drying Temperature	120 - 150	°C	
Drying Time	3.0 - 5.0	hr	
Hopper Temperature	< 100	°C	

Rear Temperature	360	°C
Middle Temperature	365 - 370	°C
Front Temperature	375	°C
Nozzle Temperature	380	°C
Mold Temperature	170 - 200	°C

Injection instructions

Runner: Die / nozzle >3mm, manifold >3.5mm Gate: >2mm or 0.5 x part thickness

NOTE

1. Crystalline
2. Mold temperature: 180°C, melt temperature: 380°C
3. 380°C nozzle

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

