

REV Materials 8004-001

Polypropylene

REV Materials

Message:

1.5% multi-walled carbon nanotubes dispersed in a polypropylene matrix suitable injection molding applications.

General Information			
Filler / Reinforcement	Carbon Nano filler, 1.5% filler by weight		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	0.918	g/cm ³	ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	2030	MPa	ASTM D638
Tensile Strength	35.9	MPa	ASTM D638
Tensile Elongation (Break)	6.0	%	ASTM D638
Flexural Modulus	1860	MPa	ASTM D790
Flexural Strength	55.8	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	16	J/m	ASTM D256
Unnotched Izod Impact	410	J/m	ASTM D256
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	2.0E+12	ohms	ASTM D257
Volume Resistivity	1.6E+12	ohms·cm	ASTM D257
Injection	Nominal Value	Unit	
Rear Temperature	149 - 232	°C	
Middle Temperature	149 - 232	°C	
Front Temperature	149 - 232	°C	
Nozzle Temperature	149 - 232	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT