

# MAJORIS CW214

Polypropylene

AD majoris

## Message:

CW214 is a 20% glass/mineral reinforced polypropylene compound intended for injection moulding.

The product is available in both black (CW214 - 8229) and natural (CW214) but other colours can be provided on request.

CW214 has been developed especially for the automotive applications and electrical components.

## APPLICATIONS

Products requiring very good long term heat resistance, high heat distortion temperature, excellent rigidity, low shrinkage and high dimensional stability can suitably be made from CW214.

Air blower wheel

Miscellaneous technical components

Electrical parts

General Information			
Filler / Reinforcement	Glass \mineral, 20% filler by weight		
Additive	heat stabilizer		
Features	Good dimensional stability		
	Rigidity, high		
	Recyclable materials		
	Heat resistance, high		
	Thermal Stability		
	Low shrinkage		
Uses	Electrical components		
	Application in Automobile Field		
Appearance	Black		
	Available colors		
	Natural color		
Forms	Particle		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.05	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	3.0	g/10 min	ISO 1133
Molding Shrinkage	0.70 - 1.1	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Break)	50.0	MPa	ISO 527-2/5
Tensile Strain (Break)	4.0	%	ISO 527-2/5
Flexural Modulus <sup>1</sup>	3100	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method

Charpy Notched Impact Strength			ISO 179/1eA
-40°C	5.0	kJ/m <sup>2</sup>	ISO 179/1eA
23°C	6.0	kJ/m <sup>2</sup>	ISO 179/1eA
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, not annealed	155	°C	ISO 75-2/B
1.8 MPa, not annealed	129	°C	ISO 75-2/A
Thermal Stability (150°C)	> 700.0	hr	
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
Glow Wire Flammability Index (2.00 mm)	750	°C	IEC 60695-2-12
Injection	Nominal Value	Unit	
Drying Temperature	80.0	°C	
Drying Time	3.0	hr	
Processing (Melt) Temp	220 - 270	°C	
Mold Temperature	30.0 - 60.0	°C	
Injection Rate	Moderate		
Injection instructions			
Holding pressure: 50 to 70% of the injection pressure			
NOTE			
1.	2.0 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

#### Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT