

STABAMID® 25 RS 6

Polyamide 66

Solvay Polyamide & Intermediates

Message:

Full-dull

| General Information | | |
|--|----------------------|--------------------|
| Uses | Textile Applications | |
| Forms | Pellets | |
| Physical | Nominal Value | Unit |
| Density | 1.14 | g/cm ³ |
| Apparent Density | 0.70 | g/cm ³ |
| Humidity - at Packaging | < 0.40 | % |
| Relative Viscosity | | |
| Formic Acid 90% | 41.0 | |
| Sulfuric Acid 96% | 2.51 | |
| Viscosity | | |
| Formic Acid 90% | 122 | cm ³ /g |
| Sulfuric Acid 96% | 135 | cm ³ /g |
| Amino End Groups | 49 | meq/kg |
| Carboxyl End Groups | 83.5 | meq/kg |
| Granulometry ¹ | 3.00 | |
| Thermal | Nominal Value | Unit |
| Melting Temperature ² | 257 | °C |
| Peak Crystallization Temperature (DSC) | 214 | °C |
| NOTE | | |
| 1. | g/100 chips | |
| 2. | 2nd melting | |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT