

RONFALIN® ST65

Acrylonitrile Butadiene Styrene

A. Schulman Europe

Message:

RONFALIN® ST65 is an Acrylonitrile Butadiene Styrene (ABS) material. It is available in Africa & Middle East, Asia Pacific, Europe, Latin America, or North America.

Important attributes of RONFALIN® ST65 are:

- Flame Rated
- RoHS Compliant
- Impact Resistant

Typical application of RONFALIN® ST65: Tools

General Information			
Features	High Impact Resistance		
Uses	Power/Other Tools		
RoHS Compliance	RoHS Compliant		
Physical	Nominal Value	Unit	Test Method
Density	1.03	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	7.0	g/10 min	ISO 1133
Molding Shrinkage	0.40 to 0.60	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	40.0	MPa	ISO 527-2/50
Flexural Modulus	1700	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact Strength	32	kJ/m²	ISO 180/1A
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	86.0	°C	ISO 75-2/B
1.8 MPa, Unannealed	84.0	°C	ISO 75-2/A
Vicat Softening Temperature	91.0	°C	ISO 306/B50
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+16	ohms	IEC 60093
Electric Strength	> 25	kV/mm	IEC 60243-1
Comparative Tracking Index (Solution A)	> 600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.60 mm)	HB		UL 94

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

