

LNP™ STAT-KON™ DE003ER compound

Polycarbonate

SABIC Innovative Plastics

Message:

LNP STAT-KON* DE003ER is a compound based on Polycarbonate resin containing Carbon Fiber. Added features of this material include: Easy Molding.

Also known as: LNP* STAT-KON* Compound DC-1003 EM MR

Product reorder name: DE003ER

General Information			
Filler / Reinforcement	Carbon fiber reinforced material		
Features	Good formability		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.24	g/cm ³	ASTM D792, ISO 1183
Molding Shrinkage			
Flow: 24 hours	0.040 - 0.10	%	ASTM D955
Transverse flow: 24 hours	0.30 - 0.40	%	ASTM D955
Vertical flow direction: 24 hours	0.32 - 0.41	%	ISO 294-4
Flow direction: 24 hours	0.040 - 0.13	%	ISO 294-4
Water Absorption (24 hr, 50% RH)	0.16	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	8780	MPa	ASTM D638
--	8410	MPa	ISO 527-2/1
Tensile Strength			
Fracture	110	MPa	ASTM D638
Fracture	109	MPa	ISO 527-2
Tensile Elongation			
Fracture	2.1	%	ASTM D638
Fracture	2.0	%	ISO 527-2
Flexural Modulus			
--	7790	MPa	ASTM D790
--	8040	MPa	ISO 178
Flexural Strength			
--	183	MPa	ASTM D790
--	177	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			
23°C	74	J/m	ASTM D256
23°C ²	6.4	kJ/m ²	ISO 180/1A
Unnotched Izod Impact			

23°C	490	J/m	ASTM D4812
23°C ³	33	kJ/m ²	ISO 180/1U
Instrumented Dart Impact			
23°C, Energy at Peak Load	15.5	J	ASTM D3763
--	3.36	J	ISO 6603-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
0.45 MPa, unannealed, 3.20mm	145	°C	ASTM D648
1.8 MPa, unannealed, 3.20mm	137	°C	ASTM D648
1.8 MPa, unannealed, 64.0mm span ⁴	146	°C	ISO 75-2/Af
Linear thermal expansion coefficient			ASTM E831, ISO 11359-2
Flow: -40 to 40°C	1.8E-5	cm/cm/°C	ASTM E831, ISO 11359-2
Lateral: -40 to 40°C	5.0E-5	cm/cm/°C	ASTM E831, ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+2 - 1.0E+5	ohms	ASTM D257
Injection	Nominal Value	Unit	
Drying Temperature	121	°C	
Drying Time	4.0	hr	
Suggested Max Moisture	0.020	%	
Rear Temperature	293 - 304	°C	
Middle Temperature	310 - 321	°C	
Front Temperature	321 - 332	°C	
Processing (Melt) Temp	304 - 327	°C	
Mold Temperature	82.2 - 110	°C	
Back Pressure	0.172 - 0.344	MPa	
Screw Speed	30 - 60	rpm	
NOTE			
1.	50 mm/min		
2.	80*10*4		
3.	80*10*4		
4.	80*10*4 mm		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT