

SEQUEL® 1718 FP BLK

Thermoplastic Polyolefin Elastomer

LyondellBasell Industries

Message:

Sequel 1718 FP BLK medium high melt flow, medium high flexural modulus, mineral-filled thermoplastic elastomeric olefin (TEO) resin has an excellent balance of properties.

General Information		
Filler / Reinforcement	Mineral filler	
Features	Medium liquidity	
Uses	Application in Automobile Field	
	Automotive exterior parts	
Processing Method	Injection molding	
Physical	Nominal Value	Unit
Density ¹ (23°C)	1.05	g/cm ³
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	15	g/10 min
Mechanical	Nominal Value	Unit
Tensile Strength ² (Yield, 23°C)	20.0	MPa
Flexural Modulus ³ (23°C)	1600	MPa
Thermal	Nominal Value	Unit
Deflection Temperature Under Load (0.45 MPa, Unannealed)	89.0	°C
NOTE		
1.	Method A	
2.	50 mm/min	
3.	2.0 mm/min	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT