

XYLEX™ X7519HP resin

Polycarbonate + Polyester

SABIC Innovative Plastics

Message:

Good Chemical Resistance, XYLEX grade with good dishwasher performance, USA/Europe Food Contact Comment: While molding of thicker parts, cooling speed has an influence of transparency. Thicker parts may form opaque areas in the centre due to slow cooling.

General Information			
Features	Good chemical resistance		
	Compliance of Food Exposure		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.19	g/cm ³	ASTM D792, ISO 1183
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	13	g/10 min	ASTM D1238
Melt Volume-Flow Rate (MVR) (300°C/1.2 kg)	10.0	cm ³ /10min	ISO 1133
Molding Shrinkage - Flow (3.20 mm)	0.70 - 0.80	%	Internal method
Water Absorption			ISO 62
Saturated, 23°C	0.16	%	ISO 62
Equilibrium, 23°C, 50% RH	0.14	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			
-- ¹	2470	MPa	ASTM D638
--	2370	MPa	ISO 527-2/1
Tensile Strength			
Yield ²	58.0	MPa	ASTM D638
Yield	61.0	MPa	ISO 527-2/50
Fracture ³	66.0	MPa	ASTM D638
Fracture	66.0	MPa	ISO 527-2/50
Tensile Elongation			
Yield ⁴	2.0	%	ASTM D638
Yield	6.0	%	ISO 527-2/50
Fracture ⁵	120	%	ASTM D638
Fracture	130	%	ISO 527-2/50
Flexural Modulus			
50.0mm span ⁶	2240	MPa	ASTM D790
-- ⁷	2030	MPa	ISO 178
Flexural Stress			
--	90.0	MPa	ISO 178
Yield, 50.0mm span ⁸	98.0	MPa	ASTM D790

Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength ⁹ (23°C)	13	kJ/m ²	ISO 179/1eA
Notched Izod Impact			
-30°C	100	J/m	ASTM D256
23°C	700	J/m	ASTM D256
-30°C ¹⁰	8.0	kJ/m ²	ISO 180/1A
23°C ¹¹	10	kJ/m ²	ISO 180/1A
Instrumented Dart Impact (23°C, Total Energy)	74.0	J	ASTM D3763
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
1.8 MPa, unannealed, 3.20mm	113	°C	ASTM D648
1.8 MPa, unannealed, 64.0mm span ¹²	112	°C	ISO 75-2/Af
Vicat Softening Temperature			
--	130	°C	ASTM D1525, ISO 306/B50 ¹³
--	132	°C	ISO 306/B120
Linear thermal expansion coefficient			
Flow: -40 to 40°C	6.5E-5	cm/cm/°C	ASTM E831
Flow: -40 to 40°C	7.5E-5	cm/cm/°C	ISO 11359-2
Lateral: -40 to 40°C	6.7E-5	cm/cm/°C	ASTM E831
Lateral: -40 to 40°C	7.5E-5	cm/cm/°C	ISO 11359-2
Injection	Nominal Value	Unit	
Drying Temperature	85.0 - 100	°C	
Drying Time	2.0 - 3.0	hr	
Drying Time, Maximum	8.0	hr	
Suggested Max Moisture	0.020	%	
Suggested Shot Size	40 - 80	%	
Hopper Temperature	50.0	°C	
Rear Temperature	275 - 285	°C	
Middle Temperature	280 - 290	°C	
Front Temperature	290 - 300	°C	
Nozzle Temperature	280 - 290	°C	
Processing (Melt) Temp	280 - 300	°C	
Mold Temperature	65.0 - 75.0	°C	
Back Pressure	0.100 - 0.500	MPa	
Screw Speed	20 - 100	rpm	
NOTE			
1.	5.0 mm/min		
2.	Type 1, 50mm/min		
3.	Type 1, 50mm/min		
4.	Type 1, 50mm/min		
5.	Type 1, 50mm/min		

6.	1.3 mm/min
7.	2.0 mm/min
8.	1.3 mm/min
9.	80*10*4 sp=62mm
10.	80*10*4
11.	80*10*4
12.	80*10*4 mm
13.	标准 B (120°C/h), 载荷2 (50N)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

