

RTP 603 FR

Acrylonitrile Butadiene Styrene
RTP Company

Message:
Glass Fiber - Flame Retardant

General Information			
Filler / Reinforcement	Glass fiber reinforced material, 20% filler by weight		
Features	Flame retardancy		
RoHS Compliance	Contact manufacturer		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.36	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.20 mm)	0.10 - 0.30	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.15	%	ASTM D570
Moisture Content	0.10	%	
Primary Additive	20	%	
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	103		ASTM D785
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	6550	MPa	ASTM D638
Tensile Strength	72.4	MPa	ASTM D638
Tensile Elongation (Yield)	2.0	%	ASTM D638
Flexural Modulus	5860	MPa	ASTM D790
Flexural Strength	103	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.20 mm)	53	J/m	ASTM D256
Unnotched Izod Impact (3.20 mm)	270	J/m	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	110	°C	ASTM D648
1.8 MPa, not annealed	104	°C	ASTM D648
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	> 1.0E+15	ohms · cm	ASTM D257
Dielectric Strength ¹ (in Oil)	16	kV/mm	ASTM D149
Dielectric Constant (1 MHz)	3.50		ASTM D150
Dissipation Factor (1 MHz)	0.010		ASTM D150
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.50 mm)	V-0		UL 94
Injection	Nominal Value	Unit	

Drying Temperature	82.2	°C
Drying Time	2.0	hr
Dew Point	-17.8	°C
Processing (Melt) Temp	204 - 238	°C
Mold Temperature	62.8 - 85.0	°C
Injection Pressure	68.9 - 103	MPa

Injection instructions

Desiccant Type Dryer Required.

NOTE

1. Method A (short time)

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

