

RTP 4799 X 115376 F

Polytrimethylene Terephthalate
RTP Company

Message:
Biobased Polyester - Glass Fiber - PTFE Lubricated - 20% Bio-Content

General Information			
Filler / Reinforcement	Glass fiber reinforced material		
Additive	PTFE lubricant		
Features	Updatable resources		
	Lubrication		
RoHS Compliance	Contact manufacturer		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.69	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.20 mm)	0.30	%	ASTM D955
Moisture Content	0.010	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	124	MPa	ASTM D638
Tensile Elongation (Yield)	3.0	%	ASTM D638
Flexural Modulus	9650	MPa	ASTM D790
Flexural Strength	193	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (3.20 mm)	80	J/m	ASTM D256
Unnotched Izod Impact (3.20 mm)	640	J/m	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	218	°C	ASTM D648
1.8 MPa, not annealed	204	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating (1.50 mm, ** Values per RTP Company testing.)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	127	°C	
Drying Time	4.0 - 6.0	hr	
Dew Point	-40.0	°C	
Processing (Melt) Temp	232 - 260	°C	
Mold Temperature	87.8 - 121	°C	
Injection Pressure	68.9 - 103	MPa	

Injection instructions

Desiccant Type Dryer Required.

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

