

SEQUEL® 1733 FP BLK

Polypropylene
LyondellBasell Industries

Message:

Sequel 1733 FP BLK thermoplastic polyolefin is typically used for large automotive exterior applications that require dimensional stability over a broad temperature range.

General Information		
Features	Good dimensional stability	
Uses	Application in Automobile Field	
	Automotive exterior parts	
Processing Method	Injection molding	
Physical	Nominal Value	Unit
Density (23°C)	1.07	g/cm ³
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	14	g/10 min
Mechanical	Nominal Value	Unit
Tensile Strength ¹ (Yield, 23°C)	20.0	MPa
Flexural Modulus ² (23°C)	1850	MPa
Impact	Nominal Value	Unit
Multi-Axial Instrumented Impact Energy ³ (23°C, 3.20 mm)	17.0	J
NOTE		
1.	50 mm/min	
2.	2.0 mm/min	
3.	2.2 m/sec	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT