

Spartech Polycom PP5340

Polypropylene Homopolymer
Spartech Polycom

Message:

Spartech Polycom PP5340 is a polypropylene homopolymer (PP Homopoly) product, which contains 40% mica filler. It is available in North America. Features include:
Good processability
anti-warping
Good dimensional stability
Good stiffness

General Information			
Filler / Reinforcement	Mica filler, 40% filler by weight		
Features	Good dimensional stability		
	Low warpage		
	Rigid, good		
	Workability, good		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.24	g/cm ³	ASTM D792
Molding Shrinkage - Flow (3.18 mm)	0.80	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	33.8	MPa	ASTM D638
Tensile Elongation			ASTM D638
Yield	3.0	%	ASTM D638
Fracture	10	%	ASTM D638
Flexural Modulus - Secant	3030	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C)	27	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
0.45 MPa, not annealed	138	°C	ASTM D648
1.8 MPa, not annealed	82.2	°C	ASTM D648
Additional Information			

Flexural Modulus, ASTM D790, Tangent: 580000 psi

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

