

Cawiton® SN920

Styrene Ethylene Butylene Styrene Block Copolymer

Wittenburg B.V.

Message:

Cawiton SN920 is a Styrene Ethylene Butylene Styrene Block Copolymer (SEBS) material. It is available in Europe for injection molding. Primary attribute of Cawiton SN920: Copolymer.

General Information			
Features	Block Copolymer		
Appearance	Opaque		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.17	g/cm ³	ISO 2781
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	1.9	g/10 min	ISO 1133
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	20		ISO 868
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress			ISO 37
Across Flow : 100% Strain	0.600	MPa	
Flow : 100% Strain	0.700	MPa	
Across Flow : 200% Strain	0.800	MPa	
Flow : 200% Strain	1.00	MPa	
Across Flow : 300% Strain	1.10	MPa	
Flow : 300% Strain	1.20	MPa	
Tensile Stress			ISO 37
Across Flow : Yield	4.00	MPa	
Flow : Yield	1.90	MPa	
Tensile Elongation			ISO 37
Across Flow : Break	890	%	
Flow : Break	730	%	
Tear Strength			ISO 34-1
Across Flow	17	kN/m	
Flow	13	kN/m	
Compression Set (70°C, 22 hr)	32	%	ISO 815
Thermal	Nominal Value	Unit	Test Method
Melting Temperature (DSC) ¹	166	°C	DSC
Injection	Nominal Value	Unit	
Hopper Temperature	30.0 to 60.0	°C	
Rear Temperature	160 to 200	°C	

Middle Temperature	170 to 210	°C
Front Temperature	170 to 210	°C
Nozzle Temperature	180 to 220	°C
Processing (Melt) Temp	160 to 220	°C
Mold Temperature	20.0 to 40.0	°C

NOTE

1.
- Measured with a differential scanning calorimeter

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

