

Cevian®-N NF012A

Styrene Acrylonitrile

Daicel Polymer Ltd.

Message:

Cevian® -N NF012A is a Styrene Acrylonitrile (SAN) material. It is available in Asia Pacific. Primary attribute of Cevian® -N NF012A: Flame Rated.

General Information			
UL YellowCard	E47773-239882		
Physical	Nominal Value	Unit	Test Method
Density	1.11	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	60	g/10 min	ISO 1133
Molding Shrinkage - Flow	0.30 to 0.50	%	ASTM D955
Water Absorption (23°C, 24 hr)	0.30	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	79		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Yield)	69.0	MPa	ISO 527-2
Flexural Modulus	3600	MPa	ISO 178
Flexural Stress	100	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	2.0	kJ/m ²	ISO 179/1eA
Notched Izod Impact (23°C, 6.40 mm)	20	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			
1.8 MPa, Unannealed, 12.7 mm	87.0	°C	ASTM D648
1.8 MPa, Unannealed	75.0	°C	ISO 75-2/A
Vicat Softening Temperature	85.0	°C	ISO 306/B50
CLTE - Flow	7.0E-5	cm/cm/°C	ISO 11359-2
Ball Pressure Test	85	°C	
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength (1.50 mm)	25	kV/mm	ASTM D149
Arc Resistance (3.00 mm)	125	sec	ASTM D495
Arc Resistance (3.00 mm)	PLC 5		ASTM D495
Flammability	Nominal Value	Unit	Test Method
Flame Rating (1.70 mm)	V-2		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	70.0 to 80.0	°C	
Drying Time	3.0 to 4.0	hr	
Rear Temperature	150 to 160	°C	

Middle Temperature	160 to 170	°C
Front Temperature	170 to 190	°C
Nozzle Temperature	170 to 190	°C
Mold Temperature	40.0 to 60.0	°C
Back Pressure	5.00 to 15.0	MPa
Screw Speed	40 to 60	rpm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

