

EcoPaXX® Q-E7300

Polyamide 410
DSM Engineering Plastics

Message:

EcoPaXX® Q-E7300 is a Polyamide 410 (Nylon 410) material. It is available in Asia Pacific, Europe, or North America for extrusion. Primary attribute of EcoPaXX® Q-E7300: Eco-Friendly/Green.

Typical application of EcoPaXX® Q-E7300: Hose/Tubing

General Information				
Features		Renewable Resource Content		
Uses		Tubing		
Processing Method		Extrusion		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.05	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow	1.8	--	%	
Flow	2.8	--	%	
Water Absorption (Equilibrium, 23°C, 50% RH)	1.7	--	%	ISO 62
Calculated Bio-based Carbon Content	56	--	%	ASTM D6866
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	1800	900	MPa	ISO 527-2
Tensile Stress (Yield)	50.0	35.0	MPa	ISO 527-2
Tensile Strain (Yield)	6.0	20	%	ISO 527-2
Nominal Tensile Strain at Break	30	> 50	%	ISO 527-2
Flexural Modulus	1750	950	MPa	ISO 178
Flexural Stress	70.0	40.0	MPa	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	20	--	kJ/m ²	
23°C	65	75	kJ/m ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	No Break	--		
23°C	No Break	No Break		
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, Unannealed	140	--	°C	ISO 75-2/B
1.8 MPa, Unannealed	75.0	--	°C	ISO 75-2/A

Melting Temperature ¹	250	--	°C	ISO 11357-3
CLTE				ISO 11359-2
Flow	1.4E-4	--	cm/cm/°C	
Transverse	1.2E-4	--	cm/cm/°C	
Injection	Dry	Unit		
Drying Temperature	80.0		°C	
Drying Time	4.0 to 8.0		hr	
Rear Temperature	250 to 270		°C	
Middle Temperature	260 to 280		°C	
Front Temperature	270 to 290		°C	
Nozzle Temperature	270 to 300		°C	
Processing (Melt) Temp	270 to 300		°C	
Mold Temperature	60.0 to 100		°C	
Injection Rate	Moderate-Fast			
Back Pressure	3.00 to 10.0		MPa	
Screw Compression Ratio	2.5:1.0			
NOTE				
1.	10°C/min			

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

