

Desmopan® DP 9868DU

Thermoplastic Polyurethane Elastomer (Polyether)

Covestro - PUR

Message:

Extrusion- and injection molding grade; very good hydrolysis and microbial resistance; very good low-temperature impact strength; opaque; Cylindrical pellets; Application; Boot shells; Technical parts

General Information			
Features	Hydrolysis Resistant		
	Low Temperature Impact Resistance		
	Microbe Resistant		
Uses	Engineering Parts		
RoHS Compliance	RoHS Compliant		
Appearance	Opaque		
Processing Method	Extrusion		
	Injection Molding		

Physical	Nominal Value	Unit	Test Method
Density (23°C)	1.17	g/cm ³	ISO 1183

Hardness	Nominal Value	Unit	Test Method
Shore Hardness			ISO 868
Shore A, 23°C	98		
Shore D, 23°C	65		

Mechanical	Nominal Value	Unit	Test Method
Tensile Stress ¹			DIN 53504
Break, 23°C	52.0	MPa	
10% Strain, 23°C	21.0	MPa	
50% Strain, 23°C	25.0	MPa	
100% Strain, 23°C	28.0	MPa	
300% Strain, 23°C	43.0	MPa	
Tensile Strain ² (Break, 23°C)	370	%	DIN 53504
Flexural Modulus ³ (23°C)	548	MPa	ISO 178
Abrasion Resistance (23°C)	37.0	mm ³	ISO 4649-A
Tensile Storage Modulus			ISO 6721-1,-4
-20°C	1.20	GPa	
20°C	0.684	GPa	
60°C	0.268	GPa	
Impact Resilience (23°C)	53	%	ISO 4662

Elastomers	Nominal Value	Unit	Test Method
------------	---------------	------	-------------

Tear Strength ⁴ (23°C)	160	kN/m	ISO 34-1
Compression Set			ISO 815
23°C, 72 hr	48	%	
70°C, 24 hr	55	%	
Injection	Nominal Value	Unit	
Drying Temperature	< 110	°C	
Processing (Melt) Temp	225 to 235	°C	
Mold Temperature	40.0 to 60.0	°C	
NOTE			
1.	200 mm/min		
2.	200 mm/min		
3.	2.0 mm/min		
4.	500 mm/min		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

