

Bergamid™ B800 H white 1 UV

Polyamide 6
PolyOne Corporation

Message:

Bergamid™ B800 H white 1 UV is a Polyamide 6 (Nylon 6) product. It is available in Africa & Middle East, Asia Pacific, or Europe.
Characteristics include:
RoHS Compliant
Good UV Resistance
Heat Resistant
High Viscosity

General Information			
Features	Good Heat Aging Resistance		
	Good UV Resistance		
	High Viscosity		
RoHS Compliance	RoHS Compliant		
Forms	Pellets		
Physical	Nominal Value	Unit	Test Method
Density ¹	1.13	g/cm ³	DIN 53479
K-Value ²	> 80.0		
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (23°C, 4.00 mm, Injection Molded)	3200	MPa	ISO 527-2/1
Tensile Stress (Yield, 23°C, 4.00 mm, Injection Molded)	85.0	MPa	ISO 527-2/50
Tensile Strain (Yield, 23°C, 4.00 mm, Injection Molded)	3.5	%	ISO 527-2/50
Flexural Modulus (23°C)	2500	MPa	ISO 178
Flexural Stress (23°C)	79.0	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-30°C	2.7	kJ/m ²	
23°C	3.5	kJ/m ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-30°C	66	kJ/m ²	
23°C	No Break		
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature			
0.45 MPa, Unannealed	170	°C	ISO 75-2/B
1.8 MPa, Unannealed	65.0	°C	ISO 75-2/A
Maximum Use Temperature			IEC 60216
-- ³	75	°C	

Short Time	175	°C	
Melting Temperature (DSC)	223	°C	ISO 3146
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+14	ohms	IEC 60093
Volume Resistivity	1.0E+15	ohms·cm	IEC 60093
NOTE			
1.	±0.03 g/cm ³		
2.	96% H ₂ SO ₄		
3.	Continuous (GTP 50% Tensile)		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

