

LubriOne™ MP-20GF/15T BLACK

Polyphenylene Ether + PS
PolyOne Corporation

Message:
PTFE lubricated

General Information			
UL YellowCard	E76261-102236145		
Filler / Reinforcement	Glass fiber reinforced material, 20% filler by weight		
Additive	PTFE lubricant		
Features	Lubrication		
Appearance	Black		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.31	g/cm ³	ASTM D792
Molding Shrinkage - Flow	0.20 - 0.40	%	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus ¹	5850	MPa	ASTM D638
Tensile Strength ²	90.0	MPa	ASTM D638
Tensile Elongation ³ (Break)	3.5	%	ASTM D638
Flexural Modulus ⁴	6050	MPa	ASTM D790
Flexural Strength ⁵	140	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.20 mm)	90	J/m	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed, 3.20 mm)	135	°C	ASTM D648
Flammability	Nominal Value		Test Method
Flame Rating (1.60 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	90.0 - 100	°C	
Drying Time	3.0 - 4.0	hr	
Rear Temperature	270 - 300	°C	
Middle Temperature	270 - 300	°C	
Front Temperature	270 - 300	°C	
Mold Temperature	65.0 - 95.0	°C	
Injection instructions			
Injection Pressure: MED-HIGHHold Pressure: MED-HIGHScrew Speed: MODERATEBack Pressure: LOW			
NOTE			
1.	5.0 mm/min		

2.	5.0 mm/min
3.	5.0 mm/min
4.	1.3 mm/min
5.	1.3 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

