

# KYOCERA TCG1604

Thermoset, Unspecified

KYOCERA Chemical Corporation

## Message:

"TCG1800 series" have an Excellent Flexibility and can Encapsulate Parts Sensitive to the Stress.

Strong Points

Cured Resin have an Excellent Flexibility so this resin can encapsulate Parts sensitive to the Stress.

Excellent Electrical Insulation Property.

Long Pot Life and Excellent Workability.

Application

Encapsulation for Module Parts , Ferrite Parts and Substrate of Ceramics, etc.

General Information		
Features	Electrically Insulating	
	Good Flexibility	
Uses	Electrical/Electronic Applications	
Processing Method	Casting	
	Encapsulating	
Hardness	Nominal Value	
Durometer Hardness (Shore D, 25°C)	90	
Thermal	Nominal Value	Unit
Glass Transition Temperature	125	°C
Electrical	Nominal Value	Unit
Volume Resistivity (25°C)	1.6E+16	ohms·cm
Dielectric Strength (25°C)	> 25	kV/mm

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

## Recommended distributors for this material

### Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

