

SIBUR Synthetic Rubber SKN 3365 E

Acrylonitrile Butadiene Rubber

SIBUR, LLC

Message:

SKN 3365 E is essentially an acrylonitrile (31-35 %) and 1,3-butadiene copolymer obtained by emulsion polymerization method at a temperature of 32 °C with the use of phytogenous fatty acid soaps as emulsifier in accordance with the ecologically clean technology. High Mooney viscosity, medium content of acrylonitrile, heightened oil resistance.

Application

The manufacturing of cables, packing, sleeve gaskets, fuel hoses, roll and chemical equipment coatings, technical plates, adhesives.

General Information			
Additive	Antioxidation 2		
Features	Antioxidation		
	Fuel resistance		
	Oil resistance		
	Viscosity, High		
Uses	Wire and cable applications		
	Washer		
	Pipe		
	Coating application		
	Adhesive		
Appearance	Yellow		
Forms	Pack 3		
Physical	Nominal Value	Unit	Test Method
Mooney Viscosity (ML 1+4, 100°C)	62 - 68	MU	Internal method
Acrylonitrile Content	31.0 - 35.0	%	Internal method
Ash Content		%	Internal method
Volatile Matter		%	Internal method
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ¹	> 23.5	MPa	Internal method
Tensile Elongation ² (Break)	> 450	%	Internal method
Additional Information			
Recipe (Mass fraction):			
Rubber = 100.0			
Technical stearic acid acc. GOST 6484, grades T-18 or T-32 = 1.0			
Dry zink oxide acc. GOST 202, grade BCOM = 3.0			
Vulcanizing accelerator TBBS acc. Specifications TY 2491-055-05761637 = 0.7			
Carbon black acc. GOST 7885, grade P-324 = 40.0			
Technical sulfur acc. GOST 127.4, grade 9995 or 9990, class 1 or 2 = 1.5			
Total = 146.2			
NOTE			

- | | |
|----|--|
| 1. | Vulcanization mode of samples:
142° × 50 min. |
| 2. | Vulcanization mode of samples:
142° × 50 min. |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

