

TAROMID A 280 G2 Y0

Polyamide 66

Taro Plast S.p.A.

Message:

Polyamide 66 glass medium viscosity 10% glassfibres reinforced, heat stabilized, halogen free flame retardant UL94 V0, high electrical properties, good flow and mechanical properties as well as dimensional stability.

General Information			
UL YellowCard	E143048-100072693		
Filler / Reinforcement	Glass fiber reinforced material, 10% filler by weight		
Additive	heat stabilizer		
	Flame retardancy		
Features	Good dimensional stability		
	Good liquidity		
	Thermal Stability		
	Halogen-free		
	Medium viscosity		
	Flame retardancy		
Processing Method	Injection molding		
Physical	Nominal Value	Unit	Test Method
Density	1.26 - 1.28	g/cm ³	ISO 1183
Molding Shrinkage			Internal method
Vertical flow direction	0.80 - 1.1	%	Internal method
Flow direction	0.50 - 0.90	%	Internal method
Water Absorption			ISO 62
23°C, 24 hr	0.90	%	ISO 62
Saturated, 23°C	6.6	%	ISO 62
Granule Humidity ¹		%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	5500	MPa	ISO 527-2/1
Tensile Stress (Break)	84.0	MPa	ISO 527-2/50
Tensile Strain (Break)	3.8	%	ISO 527-2/50
Flexural Modulus ²	5100	MPa	ISO 178
Flexural Stress ³	100	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (23°C)	3.5	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength (23°C)	35	kJ/m ²	ISO 179/1eU
Notched Izod Impact (23°C)	38	J/m	ASTM D256

Notched Izod Impact (23°C)	3.70	kJ/m ²	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature ⁴ (1.8 MPa, Unannealed)	206	°C	ISO 75-2/A
Continuous Use Temperature			IEC 60216
-- ⁵	120	°C	IEC 60216
-- ⁶	150	°C	IEC 60216
Vicat Softening Temperature	228	°C	ISO 306/B50
Ball Pressure Test (205°C)	Pass		IEC 60695-10-2
Melting Temperature	256	°C	ISO 11357-3
CLTE - Flow (-30 to 30°C)	3.6E-5	cm/cm/°C	ISO 11359-2
Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index (CTI)	PLC 0		UL 746
Comparative Tracking Index (Solution A)	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.750 mm	V-0		UL 94
1.50 mm	V-0		UL 94
3.00 mm	V-0		UL 94
Glow Wire Flammability Index (3.00 mm)	960	°C	IEC 60695-2-12
Glow Wire Ignition Temperature (3.00 mm)	775	°C	IEC 60695-2-13
Injection	Nominal Value	Unit	
Drying Temperature	80.0 - 90.0	°C	
Drying Time	1.0	hr	
Processing (Melt) Temp	260 - 270	°C	
Mold Temperature	70.0 - 90.0	°C	
Injection Rate	Moderate		
Injection instructions			
Pre-heat Temperature: 80 to 100°CPre-heat Time: 3 hr			
NOTE			
1.	TARO 002		
2.	1.0 mm/min		
3.	1.0 mm/min		
4.	120°C/hr		
5.	20,000 hr		
6.	Short term		

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

