

SUMILITE® PL-1626 (Punching)

Phenolic

Sumitomo Bakelite Co., Ltd.

Message:

SUMILITE®PL-1626 (Punching) is a phenolic (Phenolic) product. It is available in North America. SUMILITE®PL-1626 (Punching) applications include electrical/electronic applications, electrical appliances and coating applications. The main characteristics are: flame retardant/rated flame.

General Information			
Uses	Laminate		
	Electrical/Electronic Applications		
	Electrical appliances		
Appearance	Black		
Forms	Particle		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.35	g/cm ³	ASTM D792
Water Absorption (23°C, 24 hr)	1.4	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Flexural Strength (Yield)	130	MPa	ASTM D790
Electrical	Nominal Value	Unit	Test Method
Dielectric Strength	12	kV/mm	ASTM D149
Dielectric Constant	6.20		ASTM D150
Dissipation Factor	0.052		ASTM D150
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
Additional Information			

Tests were performed in accordance with JIS K6911Flexural Strength, JIS K6911, Flow: 160 MpaFlexural Strength, JIS K6911, Accross Flow: 130 MpaSolvent Resistivity, JIS K6911, 30 min boil: ConstantDielectric Strength, JIS K6911, Flatwise: 12 MV/mPunching Shrinkage, JIS K6911, 60°C, 150 mm length, Flow: 0.27%Punching Shrinkage, JIS K6911, 60°C, 150 mm length, Across Flow: 0.52%Punching Temperature, JIS K6911: 150°CInsulation Resistance, JIS K6911: 3e4 M ohmsInsulation Resistance JIS K6911: 4e3 M ohmsHeat Resistivity, JIS K6911, 120 min: 140°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT