

# Huaфон JF-W-3021B

Polyurethane  
Huaфон Group Co., Ltd.

Message:

General Type  
Characteristics  
Soft type, good elasticity, good smoothness, good film thickness, uniform cell structure, nonstick surface.  
Applications  
Garments

| General Information           |                      |      |
|-------------------------------|----------------------|------|
| Features                      | High Elasticity      |      |
|                               | Non-Stick            |      |
|                               | Soft                 |      |
| Uses                          | Textile Applications |      |
| Additional Information        | Nominal Value        | Unit |
| Solvents                      | DMF                  |      |
| Uncured Properties            | Nominal Value        | Unit |
| Solids Content                | 29 to 31             | %    |
| Viscosity (25°C)              | 160 to 260           | Pa·s |
| Cured Properties              | Nominal Value        | Unit |
| Tensile Modulus (100% Secant) | 3.00 to 4.00         | MPa  |
| Tensile Strength              | > 30.0               | MPa  |
| Tensile Elongation at Break   | > 550                | %    |

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material


Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT