

SCHULAMID® 66 GF 30

Polyamide 66

A. Schulman Europe

Message:

30% glass fiber reinforced PA 66

General Information				
UL YellowCard		E188844-102210969	E86615-252179	
Filler / Reinforcement		Glass fiber reinforced material, 30% filler by weight		
Processing Method		Injection molding		
Part Marking Code (ISO 11469)		>PA66-GF		
Physical	Dry	Conditioned	Unit	Test Method
Density	1.35	--	g/cm ³	ISO 1183/A
Viscosity Number	145	--	cm ³ /g	ISO 307
Hardness	Dry	Conditioned	Unit	Test Method
Ball Indentation Hardness (H 358/30)	220	--	MPa	ISO 2039-1
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	10000	6200	MPa	ISO 527-2/1A/1
Tensile Stress (Break)	180	110	MPa	ISO 527-2/1A/5
Tensile Strain (Break)	3.0	6.0	%	ISO 527-2/1A/5
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-30°C	7.0	10	kJ/m ²	ISO 179/1eA
23°C	10	18	kJ/m ²	ISO 179/1eA
Charpy Unnotched Impact Strength				ISO 179/1eU
-30°C	60	40	kJ/m ²	ISO 179/1eU
23°C	72	90	kJ/m ²	ISO 179/1eU
Notched Izod Impact				ISO 180/1A
-40°C	10	--	kJ/m ²	ISO 180/1A
23°C	7.0	--	kJ/m ²	ISO 180/1A
Unnotched Izod Impact Strength				ISO 180/1U
-40°C	60	--	kJ/m ²	ISO 180/1U
23°C	65	--	kJ/m ²	ISO 180/1U
Thermal	Dry	Conditioned	Unit	Test Method
Heat Deflection Temperature				
0.45 MPa, not annealed	250	--	°C	ISO 75-2/Bf
1.8 MPa, not annealed	250	--	°C	ISO 75-2/Af

Ball Pressure Test (140°C)	Pass	--		IEC 60695-10-2
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity	> 1.0E+15	1.0E+12	ohms	IEC 60093
Volume Resistivity	> 1.0E+13	1.0E+10	ohms·cm	IEC 60093
Comparative Tracking Index	450	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Glow Wire Flammability Index	600	--	°C	IEC 60695-2-12

Additional Information

干燥

1.)

Not for use in food contact applications2.)

Not for use in medical or pharmaceutical applications

Injection	Dry	Unit	
Drying Temperature	80		°C
Drying Time	3.0 - 4.0		hr
Suggested Max Moisture	0.040 - 0.10		%
Suggested Max Regrind	20		%
Processing (Melt) Temp	280 - 300		°C
Mold Temperature	60 - 120		°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT