

ALCUDIA® EVA PA-465

Ethylene Vinyl Acetate Copolymer

REPSOL

Message:

EVA resin ALCUDIA® PA-465 is recommended for low viscosity hot melt adhesives applications, when low viscosity and high vinyl acetate content are required. It contains antioxidant and free flowing agent.

TYPICAL APPLICATIONS

Hot Melt Adhesives

Packaging

Bookbinding

Furniture

Pressure sensitive adhesive coatings

Recommended melt temperature below 200°C to avoid the decomposition of the polymer. Processing conditions should be optimised for each production line.

General Information			
Additive	Antioxidant		
	Free Flowing Agent		
Features	Antioxidant		
	Food Contact Acceptable		
	Low Viscosity		
Uses	Adhesives		
	Coating Applications		
	Furniture		
	Packaging		
Agency Ratings		EU Food Contact, Unspecified Rating	
Physical	Nominal Value	Unit	Test Method
Density (23°C)	0.957	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	400	g/10 min	ISO 1133
Vinyl Acetate Content	33.0	wt%	
Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore A)	55		ISO 868
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress (Break)	2.00	MPa	ISO 527-2
Tensile Strain (Break)	900	%	ISO 527-2
Thermal	Nominal Value	Unit	Test Method
Melting Temperature	57.0	°C	
Ring and Ball Softening Point	78	°C	ASTM E28

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China

