

SINOF P260W

Polyphenylene Sulfide
SINOF HI-TECH MATERIAL CO. LTD

Message:
Advanced glass/mineral filled PPS compound.

General Information			
Filler / Reinforcement	Glass\Mineral		
Appearance	Black		
	Natural Color		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Density	1.96	g/cm ³	ISO 1183
Water Absorption (Equilibrium, 23°C, 50% RH)	0.020	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	120		ISO 2039-2
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	170	MPa	ISO 527-2
Tensile Strain (Break)	2.0	%	ISO 527-2
Flexural Modulus	18000	MPa	ISO 178
Flexural Stress	245	MPa	ISO 178
Impact	Nominal Value	Unit	Test Method
Unnotched Izod Impact Strength	10	kJ/m ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Heat Deflection Temperature	265	°C	ISO 75-2
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	5.0E+16	ohms·cm	ISO 167
Dielectric Strength	16	kV/mm	ASTM D149
Dielectric Constant	4.20		ASTM D150
Dissipation Factor	2.0E-3		ASTM D150
Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-0		UL 94
Injection	Nominal Value	Unit	
Processing (Melt) Temp	290 to 330	°C	
Mold Temperature	120 to 150	°C	

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection.All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT