

ESENTTIA 11H01A

Polypropylene Homopolymer
Polipropileno del Caribe S.A.

Message:

Characteristics: Medium melt flow rate Homopolymer polypropylene with good impact/stiffness balance, with antistatic additive.
Recommended for: Injection molding of rigid articles, closures, general purpose injection molding applications.

General Information			
Additive	Antistatic		
Features	Antistatic		
	Food Contact Acceptable		
	General Purpose		
	High Rigidity		
	Homopolymer		
	Medium Flow		
Uses	Closures		
	General Purpose		
Agency Ratings	EC 1907/2006 (REACH)		
	EC 1935/2004		
	EC 2023/2006		
	EU 10/2011		
	FDA 21 CFR 177.1520(a)(3)(i)(c)(1)		
	FDA 21 CFR 177.1520(b)		
Forms	Pellets		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) ¹ (230°C/2.16 kg)	13	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ² (Yield, 3.20 mm, Injection Molded)	35.2	MPa	ASTM D638
Tensile Elongation ³ (Yield, 3.20 mm, Injection Molded)	9.0	%	ASTM D638
Flexural Modulus - 1% Secant ⁴ (3.20 mm, Injection Molded)	1520	MPa	ASTM D790A
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (23°C, 3.20 mm, Injection Molded)	40	J/m	ASTM D256A

NOTE	
1.	Procedure B
2.	Type I, 50 mm/min
3.	Type I, 50 mm/min
4.	Type I, 1.3 mm/min

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519
Phone: +86 13424755533
Email: sales@su-jiao.com
No. 215, Lianhe North Road, Fengxian District, Shanghai, China



WECHAT