

Tecnoprene® 3K8EL9 NERO900

Polypropylene Copolymer

SO.F.TER. SPA

Message:

Elastomer modified polypropylene copolymer reinforced with 40% chemically coupled glass fiber

General Information			
Filler / Reinforcement	Glass Fiber,40% Filler by Weight		
Features	Chemically Coupled		
	Copolymer		
Agency Ratings	EC 1907/2006 (REACH)		
Appearance	Black		
Processing Method	Injection Molding		
Physical	Nominal Value	Unit	Test Method
Specific Gravity	1.21	g/cm ³	ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	3.5	g/10 min	ASTM D1238
Molding Shrinkage	0.30	%	Internal Method
Water Absorption (23°C, 24 hr)	0.020	%	ASTM D570
Ash Content	40	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	70.0	MPa	ASTM D638
Flexural Modulus	6200	MPa	ASTM D790
Flexural Strength	110	MPa	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact			ASTM D256
-20°C	170	J/m	
23°C	270	J/m	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (1.8 MPa, Unannealed)	145	°C	ASTM D648
CLTE - Flow	5.0E-5	cm/cm/°C	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+15	ohms	ASTM D257
Dielectric Constant (1 kHz)	2.50		ASTM D150
Comparative Tracking Index	650	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (3.20 mm)	HB		UL 94
Injection	Nominal Value	Unit	
Drying Temperature	90.0	°C	

Drying Time	3.0	hr
Rear Temperature	210	°C
Middle Temperature	240	°C
Front Temperature	250	°C
Mold Temperature	50.0 to 70.0	°C

The information and data on this page are provided by manufacturers and document providers. SHANGHAI SUSHENG assumes no legal liability. It is strongly recommended to verify all technical data with material suppliers before final material selection. All rights belong to the original authors. If any infringement occurs, please contact us immediately.

Recommended distributors for this material

Susheng Import & Export Trading Co.,Ltd.

Tel: +86 21 5895 8519

Phone: +86 13424755533

Email: sales@su-jiao.com

No. 215, Lianhe North Road, Fengxian District, Shanghai, China

